

## Sanding Sealer Quick Dry

390

SECTION NO. 4 ADS 508

Туре	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME			
						Tack Free	Re-coat	Cure	
Vinyl Toluene Linseed Oil Copolymer	Semi Gloss	Up to 450 Sq. Ft. Per Gallon	Brush, Roller or Spray	Mineral Spirits	Mineral Spirits	1 Hour	4-6 Hours	7-10 Days	
PRODUCT NAME: 390 Sanding Sealer Quick Dry		This fast dry sanding sealer provides versatility, as it may be used as a sanding sealer and finish coat. Though designed primarily as a sealer, it's cured film is extremely hard and durable, thus adapting itself as a finish coat.							
WHERE TO USE:		Wood On interior areas such as floors, trim, furniture, doors or cabinets. Not recommended fur use under Polyurethane Varnishes.							
Surface Preparation:		Surface to be coated must be clean and free of dust, grease, dirt or wax. If it was a suspect contaminate, remove with a commercial wax stripper. new interior wood must be sanded smooth and for best results apply a second coat of 2060 or 151-100 allowing 4 to 6 hours dry time before sanding and applying topcoats. On previously coated surfaces, remove any loose or scaly film and feather sand rough edges. Glossy surfaces must be dulled by sanding.							
Application:		This Semi-Gloss Sanding Sealer may be brushed, rolled or sprayed. Best rolling results are obtained with a short nap mohair roller. For best brush application, us a china bristle brush. When brushing or rolling, flow material on with a minimum of strokes. If sanding for additional coats, sand after 4 hours dry time and before 48 hours. After 48 hours dry time the film becomes very hard and sanding is difficult. Thinning is not recommended, if necessary use mineral spirits sparingly. Do not apply when surface or air temperature are below 40°F. Not for exterior or marine use.							
NOTE: Formulated without mercury or lead.									

ResinType:	Vinyl Toluene Linseed Oil Copolymer				
Solids:	Weight – 37.9% Volume – 34.0%				
Weight Per Gallon:	6.74 lbs.				
Viscosity:	25 – 30 seconds (No. 4 Ford Cup)				
Specular Gloss:	70 - 75°F @ 60 degrees				
Recommended Film Thickness:	Wet - 3.0 - 3.5 mils Dry - 1.0 - 1.2 mils				
VOC – VOS Statement:	This product contains a maximum of 3.75 lbs. or 450 GPL per gallon.				
Cautions:	WARNING! FLAMMABLE! Contains Petroleum Distillates Keep away from heat & flame. To avoid breathing vapors or spray mist, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches or dizziness, increase fresh air or wear respiratory protection (NIOSH/MSHA TC23C or equivalent) or leave the area. Close container after each use. Avoid contact with skin. Use with adequate ventilation. NOTICE: Reports have associated repeated and prolonged occupational overexposure to solvents with permanent brain & nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal.  KEEP OUT OF REACH OF CHILDREN.				