

## PRO PRIME EXTERIOR ALKYD WOOD PRIMER / SEALER 560

SECTION NO. 10 ADS 1102

Туре	Sheen	Spread Rate	Recommended Application		Clean		DRY TIME		
				Thinner	Up	Tack Free	Re-coat	Cure	
Modified Soya Alkyd	Flat	300-400 Sq Ft Per Gallon	Brush, Roller, Pad or Spray	Mineral Spirits	Mineral Spirits	2 – 3 Hours	Over- night	7 Days	
PRODUCT NAME: 560 Pro Prime Exterior Alkyd Wood Primer / Sealer		A high quality exterior primer formulated for use on exterior wood, hard board, pressure-treated lumber, factory finished wood products and previously painted wood surfaces. This flexible, mildew resistant film makes an excellent base coat for most exterior house paint. Provides good water resistance. Excellent stain resistance over cedar or redwood. Resists tannin stains, nail head rusting and moisture.							
WHERE TO USE:		Wood On exterior siding, trim, facia and fences. Hardboard Pressure Treated Lumber							
Surface Preparation:		Surface must be clean, dry and free of dirt, grease or grime. Remove all loose, peeling or flaking paint by sanding or scraping. Dull glossy surfaces by sanding. Remove any traces of mildew by washing with a solution that kills mildew spores. Prime new or unrusted galvanized metal with #50 Block It Acrylic Primer Sealer. Sand and prime weathered surfaces completely with Weather Proof Exterior Oil Primer. Prime all new wood surfaces.							
Application:		Stir product with a circular, lifting motion before you begin to paint. Oil House Paint Primer may be applied by brush, spray, pad or roller at a rate of application not to exceed 400 sq ft per gallon. Surface texture and porosity will effect actual yield. For best brush application results, use a quality natural hair bristle brush. For roller application, use a mohair ¼" or 3/8" nap cover for smooth surfaces and a ½" cover for semi-rough surfaces. Thinning is not recommended, if necessary, use mineral spirits sparingly. Do not apply if rain is threatening or if temperature is below 40°F. When priming redwood or cedar, it may be necessary to apply two coats to check tannic bleed.							
NOTE: Formulated without mercury or lead.									

Revised 08/2005

Resin Type:	Modified Soyd Alkyd			
Solids:	Weight – 76.1% Volume – 54.5%			
Weight Per Gallon:	12.44 lbs.			
Viscosity:	80 – 85 (Krebs Units)			
Specular Gloss:	2 – 3% @ 60 Degrees			
Recommended Film Thickness:	Wet – 3.5 to 4.0 mils Dry – 1.7 to 2.0 mils			
VOC – VOS Statement:	This product contains less than 2.9 lbs or 350 GPL per gallon.			
Cautions:	CAUTION! COMBUSTIBLE! Contains Petroleum Distillates Keep away from heat & flame. To avoid breathing vapors or spray mist, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches or dizziness, increase fresh air or wear respiratory protection (NIOSH/MSHA TC 23C) or equivalent) or leave the area. Close container after each use. Avoid contact with skin. Use with adequate ventilation. NOTICE: Reports have associated repeated and prolonged occupational over exposure to solvents with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal.  KEEP OUT OF REACH OF CHILDREN			

Revised 08/2005 ADS 1102

