



**MC 100
High Build
Latex Flat**

| Type | Sheen | Spread Rate | Recommended Application | Thinner | Clean Up | DRY TIME | | |
|---|-------|--|--|-------------|------------------|-----------|---------|--------|
| | | | | | | Tack Free | Re-coat | Cure |
| Latex | Flat | Up to 350 Sq Ft Per Gallon | Brush, Roller, Or Airless Spray | Clean Water | Warm Soapy Water | 1 Hour | 4 Hours | 7 Days |
| PRODUCT NAME: MC100 High Build Interior Latex Flat | | This Latex Flat Coating is designed to provide good dry hide and an excellent matte flat appearance when applied to properly prepared surfaces. Exhibits good touch-up properties. Formulated exclusively for production work such as apartment and commercial construction. | | | | | | |
| WHERE TO USE: | | Drywall Plaster Masonry Wood Metal | An dead flat coating that is ideal for use in property maintenance, apartments or for budget minded consumers. NOTE: Not for use in areas that require frequent washing. | | | | | |
| SURFACE PREPARATION: | | <p>Remove any dirt, wax, oil, mildew or dust prior to painting. Any loose or flaking paint should be removed and the edges feather sanded to produce a smooth, uniform surface. Wood or bare metal should be primed with the appropriate primer prior to finishing.</p> <p>On previously painted surfaces in good repair, no priming is generally unnecessary. Glossy surfaces should be dulled with sandpaper. Patch holes or cracks with appropriate filler. Spot prime bare areas with the appropriate primer or this product.</p> <p>Priming – Drywall – Self priming, or use 4190 Drywall Primer Plaster – 50 Block-It Primer Sealer. Wood – 50 Block-It Primer Sealer Masonry Block –529-11 Latex Block Filler.</p> | | | | | | |
| APPLICATION: | | <p>Stir product with a circular, lifting motion to disperse into a homogenous liquid. To achieve proper results use a nylon or nylon/polyester brush and a quality 3/8in – 1-1/4” nap roller. Using the shortest nap roller that will coat the wall texture provides the best coverage.</p> <p style="text-align: center;">Airless Spray – Tip atomization pressures will vary with type of equipment, viscosity and temperature. An orifice of .017 - .019 will provide the most satisfactory spray pattern.</p> <p>Best results are more likely obtained by using quality application tools. Do not apply directly over chalky surfaces or bleeding stains.</p> | | | | | | |

NOTE: Formulated without mercury or lead.

| | |
|--|--|
| RESIN TYPE: | Vinyl Acetate Acrylic Copolymer |
| SOLIDS: | Volume – 29.1 % |
| WEIGHT PER GALLON: | 11.45 lbs. |
| VISCOSITY: | 99 - 103 (Krebs Units) |
| SPECULAR GLOSS: | 40 – 50% @ 60 Degrees |
| RECOMMENDED FILM THICKNESS: | Wet – 4.6 Mils Dry – 1.3 Mils |
| VOC – VOS STATEMENT: | This product contains less than 50 grams per liter. |
| Lead Statement: | WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS A BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start find out how to protect yourself and your family by contacting the National Lead Information Hotline 1-800-424-LEAD or log on to www.epa.gov/lead . |
| <p>CAUTION!</p> <p>Do not take internally. Close container after each use.</p> <p>KEEP FROM FREEZING.</p> <p>KEEP OUT OF REACH OF CHILDREN.</p> | |

12/23

