



FINAL FINISH MASONRY SEALER

21 - 10

SECTION NO. 9 ADS 1013

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
Acrylic	Gloss * See Below	250 - 300 Sq Ft Per Gallon	Brush, Roller or Spray	Xylol	Xylol	30 Minutes	2 Hours	24 Hours
PRODUCT NAME: FINAL FINISH MASONRY SEALER 21 - 10		Decorative Stone Sealer is designed to penetrate deep into the pores of masonry surfaces to stop dusting and protect the surface from penetrating stains. It may be used on both walls (vertical surfaces) and floors (horizontal surfaces).						
WHERE TO USE:		Chattahoochee Stone On interior or exterior surfaces such as patios, entryways, walkways, floors, and walls. Flagstone Concrete Brick Sandstone						
Surface Preparation:		Surface to be coated must be clean and free of dust, grease, wax and rust. Remove all loose scaly material by sanding thoroughly. Suitable for use on previously sealed surfaces, but not recommended for use on painted surfaces. Apply a small test area of 21-10 to determine compatibility on previously sealed surfaces. New concrete must cure at least 28 days prior to sealing. New and uncoated concrete must be etched with Coronado Sur-Prep IV prior to coating.						
Application:		Decorative Stone Sealer may be applied by brush, roller or spray. Best rolling results are obtained with a short nap mohair roller. When brushing or rolling, flow material on with a minimum of strokes. Thin up to ½ pint of xylol per gallon for ideal penetration. Apply in thin coats and do not apply in direct sunlight or on hot surfaces, as gas blisters can be created by the heat turning the solvent into a gas. * When applied to a sealed surface, this product will dry to a gloss finish. A thinned coat applied over a porous surface will provide a low sheen finish.						
NOTE: Formulated without mercury or lead.								

Resin:	Acrylic								
Solids:	Weight – 20.2% Volume – 16.5%								
Weight Per Gallon:	7.59 lbs.								
Viscosity:	13 – 18 seconds (No. 4 Ford Cup)								
Flash Point:	85°F (TT-P-141, Method 4293)								
Specular Gloss:	80% ± @ 60 Degrees								
Sag Rating:	Pass 6 mils (Lenetta)								
Recommended Film Thickness:	Wet – 2.0 - 3.5 mils Dry - 0.3 - 0.6 mils								
Light Reflectance:	N / A								
VOC – VOS Statement:	This product contains a maximum of 6.05 lbs. VOC / VOS per gallon of coating.								
Cautions:	<p style="text-align: center;">WARNING ! FLAMMABLE !</p> <p style="text-align: center;">Contains Xylene and Petroleum Distillates</p> <p>Keep away from heat & flame. To avoid breathing vapors or spray mist, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches or dizziness, increase fresh air or wear respiratory protection (NIOSH/MSHA TC23C or equivalent) or leave the area. Close container after each use. Avoid contact with skin. Use with adequate ventilation. NOTICE: Reports have associated repeated and prolonged occupational overexposure to solvents with permanent brain & nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal.</p> <p style="text-align: center;">KEEP OUT OF REACH OF CHILDREN.</p>								
Chemical Abstract Number:	<table> <thead> <tr> <th>Ingredient:</th> <th>CAS. NO.</th> </tr> </thead> <tbody> <tr> <td>Acrylic Resin</td> <td>Proprietary</td> </tr> <tr> <td>Toluene</td> <td>108-88-3</td> </tr> <tr> <td>Xylene</td> <td>1330-20-7</td> </tr> </tbody> </table>	Ingredient:	CAS. NO.	Acrylic Resin	Proprietary	Toluene	108-88-3	Xylene	1330-20-7
Ingredient:	CAS. NO.								
Acrylic Resin	Proprietary								
Toluene	108-88-3								
Xylene	1330-20-7								
Federal Specification:	Meets the performance requirements of MIL – L – 47117.								