



**HEAVY DUTY
HIGH BUILD
LATEX FLAT
9200 Line**
SECTION NO. 1 ADS-210

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
Latex	Flat	Up to 350 Sq Ft Per Gallon	Airless Spray	Clean Water	Warm Soapy Water	30 Minutes	4 Hours	30 Days
PRODUCT NAME: 9200 LINE HEAVY DUTY HIGH BUILD Latex / Flat		This Latex Flat coating is designed to provide good dry hide appearance when applied to properly prepared interior surfaces. Exhibits excellent touch up characteristics.						
WHERE TO USE:		Drywall May be applied to interior surfaces where a flat finish is desirable. Plaster Wood Cement Block Stucco						
Surface Preparation:		<p>New Work: The surface to be coated must be clean and free of dust, grease, wax, rust, oil, and bleeding stains.</p> <p>Priming:</p> Drywall – Self Priming Plaster – For best results use No. 50 Block-Out Wood - Alkyd Primer Undercoat 37-11 Ferrous Metal - Rust inhibiting metal primer such as 35-111, 2090 and 925-147 Non-Ferrous Metal - Perma-Bond 100-10 Galvanized - 100-10 Masonry - Use Primer Sealer 43-10 or 48-11. To fill porous block use 946-11 Latex Block Filler <p>Repaint Work: On previously painted surfaces in good repair, no priming is generally necessary. On glossy surfaces, remove the sheen with sandpaper or steel wool. Patch holes or cracks with appropriate filler. Spot prime bare areas with indicated primer. Remove any oil, chalk, dirt, wax or dust prior to re-coating. Any loose flaking paint should be removed and the edges feather sanded to produce a smooth, uniform surface.</p>						
Application:		Stir product thoroughly with a circular, lifting motion to disperse into a homogenous liquid. Designed for application by airless spray. Brushing or rolling large areas will result in poor hiding. For best results, use as packaged. May be thinned with up to a pint of water per gallon, to reach proper spray viscosity. Reduction with water will decrease hiding and increase sagging. Airless Spray – Tip size at atomization pressures will vary with type of equipment, viscosity and temperature. An orifice of .017 - .019 will provide the most satisfactory spray pattern. Best results are more likely obtained by using quality application tools. Do not apply directly over chalky surfaces or bleeding stains.						
NOTE: Formulated without mercury or lead.								

Resin Type:	Vinyl Acetate Acrylic Copolymer
Solids:	Weight - 49% Volume - 32%
Weight Per Gallon:	11.00 lbs.
Viscosity:	83 – 85 (Krebs Units)
Specular Gloss:	0 – 5% @ 85 degrees
Recommended Film Thickness:	6 – 10 mils - 150 – 250' 10 – 15 mils - 75 – 150'
Scrub Tests:	300 + Cycles 600 + Strokes
Cautions:	CAUTION! Do not take internally. Close container after each use. KEEP OUT OF REACH OF CHILDREN.