



PRO - TECH
Latex / Eggshell Finish
3400 LINE

SECTION NO. 2 ADS 313

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
Vinyl Acrylic	Eggshell Enamel	Up to 400 Sq Ft Per Gallon	Brush, Roller, Pad or Airless Spray	Clean Water	Warm Soapy Water	60 Minutes	4 Hours	30 Days
PRODUCT NAME: 3400 LINE Pro - Tech Latex / Eggshell Enamel		Pro-Tech Eggshell Enamel is designed to be applied with equal success by contractors or do-it-yourselfers. It applies easily without spattering, covers most surfaces in one coat and may be washed repeatedly without film damage. Perfect for children's bedrooms, hallways or wherever a low sheen is desirable.						
WHERE TO USE:		Drywall Plaster Wood Metal Masonry	Pro-Tech Latex Eggshell can be applied to walls, woodwork, trim, paneling, doors or dadoes. It is a good choice for interior bedrooms, family rooms, hallways, recreation rooms, commercial or rental properties.					
Surface Preparation:		<p>New Work: The surface to be coated must be clean and free of dust, grease, wax, rust, oil, and bleeding stains.</p> <p>Priming: Drywall –For best results use #4190 Latex Primer Sealer. Plaster – For best results use #50 Block-Out Wood – Alkyd Primer Undercoat #37-11 Ferrous Metal – Rust inhibiting metal primer such as #35-111, #925-147. Galvanized/Non-Ferrous - #36-11 or #180-11. Masonry – Masonry Sealer #43-10 or #48-11. To fill porous block use #529-11 Latex Block Filler.</p> <p>Repaint Work: On previously painted surfaces in good repair, no priming is generally necessary. On glossy surfaces, remove the sheen with sandpaper or steel wool. Patch holes or cracks with appropriate filler. Spot prime bare areas with indicated primer. Remove any oil, chalk, dirt, wax or dust, prior to re-coating. Any loose or flaking paint should be removed and the edges feather sanded to produce a smooth, uniform surface.</p>						
Application:		Stir product thoroughly with a circular, lifting motion to disperse into a homogenous liquid. Roller – 3/8" to 1-1/4" nap, depending on surface texture. Brush – Nylon or polyester filament. Airless Spray – Tip size at atomization pressure will vary with type of equipment, viscosity and temperature. An orifice of .017 - .019 will provide the most satisfactory spray pattern. Best results are more likely obtained by using quality application tools. Do not apply directly over chalky surfaces or bleeding stains.						
NOTE: Formulated without mercury or lead.								

Resin Type:	Vinyl Acrylic
Solids:	Weight – 49.0% Volume – 33.0%
Weight Per Gallon:	10.9 lbs.
Viscosity:	94 – 97 (Krebs Units)
Specular Gloss:	12-18% @ 85 Degrees
Recommended Film Thickness:	Wet – 4.0 to 4.5 mils Dry – 1.7 to 1.9 mils
VOC – VOS Statement:	This product contains less than 3.17 lbs. per gallon or 250 G.P.L.
Cautions:	CAUTION! Do not take internally. Close container after each use. KEEP OUT OF REACH OF CHILDREN.