



Dry Fall
Alkyd Semi-Gloss
4040 & Bases
SECTION NO. 6 ADS 704

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
Modified Alkyd	Semi Gloss	300 Sq Ft Per Gallon	Spray	Not Recommended	Mineral Spirits	15 Minutes	4 Hours	7-10 Days
PRODUCT NAME: 4040 Dry Fall Alkyd Semi-Gloss		This synthetic dry fall enamel is designed for the journeyman spray applicator for use in airless or conventional spray equipment. Atomized spray and bounce back flash dry within eight foot fallout, reducing the need to cover floors and equipment. Spray dust may be swept up, vacuumed, or blown away.						
WHERE TO USE:		Drywall Plaster	On interior drywall, plaster, primed metal or concrete. This dryfall finish can be recoated in 4 hours on new or repaint work.					
Surface Preparation:		<p>Surface to be painted must be clean and free of dust, grease wax and rust. Remove all loose, scaly paint by sanding thoroughly. Chalky paint must be removed by scrubbing with warm soap and water and thoroughly rinsed. Glossy surfaces must be dulled by thoroughly sanding with steel wool. Any exposed substrate should be spot primed with the appropriate primer. Best possible results on repaint work are usually achieved by using two coats of Dry Fall Semi-Gloss allowing 4 hours between coats.</p> <p>Primers:</p> <ul style="list-style-type: none"> *Steel – 35-111, 35-147 Alkyd Metal Primers *Non-Ferrous Metal – 100-10 Perma Bond Primer *Wood Interior - C37-11 Undercoater *Concrete Block - C946-11 Latex Block Filler *Poured Concrete - 4190 Latex Primer *Galvanized - Acrylic 180-11 						
Application:		<p>This product may be applied by spray only, either airless or conventional. Stir thoroughly making sure no pigment remains on the bottom of the can. No thinning is recommended.</p> <p>IMPORTANT: Apply only when surface and air temperatures are between 45° and 90° F.</p>						
NOTE: Formulated without mercury or lead.								

Resin Type:	Modified Alkyd
Solids:	Weight – 72% Volume – 47%
Weight Per Gallon:	11.76 lbs.
Viscosity:	68 - 74 (Krebs Units)
Specular Gloss:	8-15% @ 60 degrees
Recommended Film Thickness:	Wet – 4.0 to 6.0 mils Dry – 1.4 to 2.1 mils
VOC – VOS Statement:	This product contains less than 3.33 lbs or 400 GPI per gallon.
Cautions:	<p>WARNING! Flammable* Contains VM & P Naphtha Keep away from heat & flame.* To avoid breathing vapors or spray mist, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches or dizziness, increase fresh air or wear respiratory protection (NIOSH/MSHA TC 23C or equivalent) or leave the area. Close container after each use. Avoid contact with skin. Use with adequate ventilation. NOTICE: reports have associated repeated and prolonged occupational over exposure to solvents with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal.</p> <p style="text-align: center;">KEEP OUT OF REACH OF CHILDREN.</p>