



HEAVY DUTY
Latex / Eggshell Finish

4400 LINE

SECTION NO. 2 ADS 345

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
Vinyl Acrylic	Eggshell	Up to 400 Sq Ft Per Gallon	Brush, Roller Pad or Spray	Clean Water	Warm Soapy Water	60 Minutes	4 Hours	30 Days
PRODUCT NAME: 4400 LINE HEAVY DUTY Latex / Eggshell Finish		This Latex Eggshell Enamel is designed to be applied with equal success by contractors or do-it-yourselfers. It applies easily without spattering, covers most surfaces in one coat, and may be washed repeatedly without film damage. Perfect for children's bedrooms, hallways or wherever a low sheen is desirable.						
WHERE TO USE:		Drywall Plaster Wood Metal Masonry Pro-Tech Latex Eggshell Enamel can be applied to walls, woodwork, trim, paneling, doors or dados. It is a good choice for interior bedrooms, family rooms, hallways, recreation rooms, commercial or rental properties.						
Surface Preparation:		Surface to be painted must be clean and free of dirt, chalk, wax, grease, rust, or loose, flaking paint. Dirt and chalk should be removed by scrubbing with warm soapy water and thoroughly rinsed with clean water. Wax should be removed with a commercial wax stripper or by solvent cleaning. Grease should be cleaned by using Coronado Sur-Prep 1. Rust must be removed by hand sanding or by conscientious power tool cleaning. Remove loose paint by scraping. Feather sand rough edges to insure a smooth finish coat. Glossy surfaces must be dulled by lightly sanding. Remove sanding dust before paint application. Any exposed substrate should be spot primed with the appropriate primer. Priming – (new or bare surfaces) Drywall – Self Priming, but for best results use 4190 Latex Primer Sealer. Plaster – For best results use No. 50 BlockOut, 2100 Sungard. Wood – Alkyd Primer Undercoat 37-11. Ferrous Metal – Rust inhibiting metal primer such as 35-111, 2090 or 925-147. Galvanized – Acrylic 36-11 or 180-11. Masonry – Masonry Sealer 43-10, 48-10, Block Filler 946-11.						
Application:		Stir product with a circular, lifting motion before you begin to paint. Pro-Tech Eggshell Enamel may be applied by brush, roller, pad or spray techniques, at a rate of application not to exceed 400 sq ft per gallon. Surface texture and porosity will effect actual yield. For best brush application results, use a quality synthetic filament brush. For roller application, use a 3/8" nap cover for smooth surfaces, and a 1/2" nap cover for semi-rough surfaces. Do not jeopardize the success of your painting project by using poor quality applicator tools. Apply only when surface and air temperatures are between 50°F and 90°F. Airless – Tip size at atomization pressures will vary with type of equipment, viscosity and temperature. An orifice of .017 - .019 will provide the most satisfactory spray pattern.						
NOTE: Formulated without mercury or lead.								

Resin:	Vinyl Acrylic
Solids:	Weight – 49.3% Volume – 33.7%
Weight Per Gallon:	10.93 lbs.
Viscosity:	90 – 95 (Krebs Units)
Specular Gloss:	20 – 25% @ 85 Degrees
Recommended Film Thickness:	Wet – 4.0 to 4.5 mils Dry - 1.3 to 1.5 mils
VOC – VOS Statement:	This product contains less than 3.17 lbs. or 250 GPL per gallon of coating.
Cautions:	CAUTION! Do not take internally. Close container after each use. KEEP OUT OF REACH OF CHILDREN.