



**PRO - TECH  
Latex / Satin Finish**

**5800 LINE**

SECTION NO. 2      ADS 315

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
Vinyl Acrylic	Satin	Up to 400 Sq Ft Per Gallon	Brush, Roller, Pad or Spray	Clean Water	Warm Soapy Water	60 Minutes	4 Hours	30 Days
<b>PRODUCT NAME:</b> 5800 LINE Latex / Satin Finish		This Latex Satin Enamel is designed to be applied with equal success by contractors or do-it-yourselfers. It applied easily without spattering, covers most surfaces in one coat and may be washed repeatedly without film damage. Perfect for children's bedrooms, hallways or wherever a low sheen is desirable.						
<b>WHERE TO USE:</b>		Drywall      Pro-Tech Latex/Satin Enamel can be applied to walls, woodwork, trim, paneling, doors or dados. It is a good choice for interior bedrooms, family rooms, hallways, recreation rooms, commercial or rental properties. Plaster Wood Metal Masonry						
<b>Surface Preparation:</b>		Surface to be painted must be clean and free of dirt, chalk, wax, grease, rust, or loose, flaking paint. Dirt and chalk should be removed by scrubbing with warm soapy water and thoroughly rinsed with clean water. Wax should be cleaned by using Coronado Sur-Prep 1. Rust must be removed by hand sanding or by conscientious power tool cleaning. Remove loose paint by scraping. Feather sand rough edges to insure a smooth finish coat. Glossy surfaces must be dulled by lightly sanding. Remove sanding dust before paint application. Any exposed substrate should be spot primed with the appropriate primer. Priming – (new or bare surfaces) Drywall – Self Priming, but for best results use 4190 Latex Primer Sealer. Plaster – For best results use No. 50 BlockOut, 2000 Sungard. Wood – Alkyd Primer Undercoat 37-11. Ferrous Metal – Rust inhibiting metal primer such as 35-111, 2090 or 925-147. Galvanized – Acrylic Primer 36-11 or 180-11. Masonry – Masonry Sealer 43-10, 48-11, Block Filler 946-11.						
<b>Application:</b>		Stir product with a circular, lifting motion before you begin to paint. Pro-Tech Satin Enamel may be applied by brush, roller, pad or spray techniques, at a rate of application not to exceed 400 sq ft per gallon. Surface texture and porosity will effect actual yield. For best brush application results, use a quality synthetic filament brush. For roller application, use a 3/8" nap cover for smooth surfaces, a 1/2" nap cover for semi-rough surfaces. Do not jeopardize the success of your painting project by using poor quality applicator tools. Apply only when surface and air temperatures are between 50°F and 90°F. <b>Airless</b> – Tip size at atomization pressures will vary with type of equipment, viscosity and temperature. An orifice of .017 - .019 will provide the most satisfactory spray pattern.						
<b>NOTE: Formulated without mercury or lead.</b>								

<b>Resin:</b>	Vinyl Acrylic
<b>Solids:</b>	Weight – 41.4% Volume – 29.0%
<b>Weight Per Gallon:</b>	10.18 lbs.
<b>Viscosity:</b>	100 – 103 (Krebs Units)
<b>Specular Gloss:</b>	20 – 25 % @ 60 Degrees
<b>Recommended Film Thickness:</b>	Wet – 4.0 to 4.5 mils Dry – 1.2 to 1.4 mils
<b>VOC – VOS Statement:</b>	This product contains less than 3.17 lbs. or 250 GPL per gallon of coating.
<b>Cautions:</b>	<p><b>CAUTION!</b> Do not take internally. Close container after each use.</p> <p><b>KEEP OUT OF REACH OF CHILDREN.</b></p>