



**ALLPRO CLEAR
POLYURETHANE
9300, 9301**
SECTION NO. 4 ADS 500

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
Poly-urethane Alkyd	Satin / Gloss	400 - 600 Sq Ft Per Gallon	Brush, Roller or Spray	Mineral Spirits	Mineral Spirits	1 Hour	4 Hours	7 - 10 Days
PRODUCT NAME: 9300, 9301 Allpro Clear Polyurethane Satin & Gloss		Allpro Polyurethane is a clear, oil modified, polyurethane coating of maximum durability. It is manufactured in both high gloss and rich satin finishes, which will substantially out-wear the finest of conventional varnishes and lacquers. This rich finish will protect and enhance the appearance of any surface. Gloss polyurethane may be used on both exterior and interior surfaces while Satin is primarily an interior product.						
WHERE TO USE:		Wood On interior areas such as floors, trim, furniture, doors or cabinets. Also on exterior semi-protected trim areas such as benches, entry doors, breezeways, etc. Not recommended for large exposed exterior vertical surfaces.						
Surface Preparation:		Gloss polyurethane should not be stirred. To thin, add 1-1/2 pints of paint thinner or turpentine to one gallon of gloss polyurethane. This acts as a sealer. Stir satin polyurethane before and during use. DON'T THIN SATIN POLYURETHANE. Brush across the grain. Finish brushing with the grain in long, even strokes. Additional coats of polyurethane help build up total film thickness for added surface protection. For best results buff well between coats. If buffing is impractical, re-coat within 24 hours. Old Work: Remove old finishes in poor condition completely and refinish as above. Old varnished surfaces should be well sanded to smooth dull condition before application of polyurethane. Shellacked surfaces should be well sanded or removed. Touch up worn areas, follow up with one or two coats.						
Application:		The polyurethane may be brushed, rolled or sprayed. Best rolling results are obtained with a short nap mohair roller. For best brush application, use a chine bristle brush. When brushing or rolling, flow material on with a minimum of strokes. Thinning is not recommended, if necessary use mineral spirits sparingly. Do not use this polyurethane varnish over wood fillers, shellacs, lacquers or any sealer that contains stearates.						
NOTE: Formulated without mercury or lead.								

Resin:	Soya Modified Aromatic Urethane									
Solids:	<table> <tr> <td></td> <td>9301</td> <td><u>9300</u></td> </tr> <tr> <td>Weight -</td> <td>50.2%</td> <td>39%</td> </tr> <tr> <td>Volume -</td> <td>47.5%</td> <td>37%</td> </tr> </table>		9301	<u>9300</u>	Weight -	50.2%	39%	Volume -	47.5%	37%
	9301	<u>9300</u>								
Weight -	50.2%	39%								
Volume -	47.5%	37%								
Weight Per Gallon:	8 lbs.									
Viscosity:	<p>9300: 11 – 13 seconds</p> <p>9301: 18 – 20 seconds, #3 Zahn Cup</p>									
Specular Gloss:	<p>9300: 25 – 30%</p> <p>9301: 93 – 98% @ 60 Degrees</p>									
Recommended Film Thickness:	<p>Wet – 3.1 to 3.6 mils</p> <p>Dry – 1.2 to 1.4 mils</p>									
VOC – VOS Statement:	This product contains less than 3.75 lbs. or 450 GPL per gallon of coating.									
Cautions:	<p>CAUTION! Combustible Contains Petroleum Distillates.</p> <p>Keep away from heat & flame. To avoid breathing vapors or spray mist, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches, or dizziness, increase fresh air or wear respiratory protection (NIOSH/MSHA TC-23C or equivalent) or leave the area. Close container after each use. Avoid contact with skin. Use with adequate ventilation. NOTICE: Reports have associated repeated and prolonged occupational over-exposure to solvents with permanent brain & nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal.</p> <p>KEEP OUT OF REACH OF CHILDREN.</p>									