



**PRO - TECH
LATEX PRIMER
L 4190 Line**

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
Acrylic Latex	Flat	Up to 400 Sq Ft Per Gallon	Brush, Roller or Spray	Clean Water	Warm Soapy Water	60 Minutes	4 Hours	7 Days
PRODUCT NAME: L 4190 Pro-Tech Latex Primer		A good quality, fast drying vinyl primer and sealer for interior drywall. It is easy to apply, low in odor, and may be top coated in four hours. It provides a good base for succeeding coats of latex or alkyd finishes. This product complies with LEED Green Building Rating System GS-11 for interior flat paints.						
WHERE TO USE:		Drywall Masonry	On interior wall surfaces prior to topcoating. Will provide an even seal and hold-out for subsequent finish coats.					
Surface Preparation:		The surface to be coated must be clean and free of dust, chalk, flaking paint, water stains or any other contaminant that could be detrimental to adhesion. Dust and chalk should be removed by brooming off, blowing with compressed air or scrubbed with warm soapy water followed by a clean rinse. Remove any flaking paint by scraping. Feather sand rough edges to insure a smooth finish coat. Glossy surfaces must be dulled by lightly sanding. Water soluble stains should be sealed with O'Leary Seal-It or Bin.						
Application:		Stir product with a circular, lifting motion before you begin to paint. May be applied by brush, roller or spray, at a rate of application not to exceed 400 square feet per gallon. Surface texture and porosity will affect actual yield. For best brush results, use a quality synthetic filament brush. For roller application, use a 3/8" nap cover for smooth surfaces, a 1/2" nap cover for semi-rough surfaces and a 3/4" nap cover for rough surfaces. For spray application, may be thinned with clean water, up to 10% reduction if necessary. Satisfactory results are most likely obtained by using quality application tools. Apply when surface temperature is above 50° F.						
NOTE: Formulated without mercury or lead.								

Resin Type:	Vinyl Acetate / Acrylic
Solids:	Weight – 44.8% Volume – 31.8%
Weight Per Gallon:	10.5 lbs.
Viscosity:	96 – 98 (Krebs Units)
Specular Gloss:	1 – 2% @ 85 degrees
Recommended Film Thickness:	Wet – 3.5 to 4.0 mils Dry – 1.1 to 1.2 mils
VOC – VOS Statement:	This product contains 50 grams per liter.
Cautions:	CAUTION! Do not take internally. Close container after each use. KEEP OUT OF REACH OF CHILDREN. KEEP FROM FREEZING.

Revised 07/2007

