



**HEAVY DUTY
Latex Flat
1088 Line**
Section No. 1 ADS – 217

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
Latex	Flat	Up to 350 Sq Ft Per Gallon	Brush, Roller, Pad or Airless Spray	Clean Water	Warm Soapy Water	30 Minutes	4 Hours	30 Days
PRODUCT NAME: 1088 Line Heavy Duty Latex / Flat		This Latex Flat Coating is designed to provide good dry hide and an excellent matte flat appearance when applied to properly prepared surfaces. Exhibits good touch-up properties. Formulated exclusively for production work such as apartment and commercial construction. This product complies with LEED Green Building Rating System GS-11 for interior non-flat paints.						
WHERE TO USE:		Drywall Plaster Wood Cement Block Metal	Primarily designed as a coating for interior wall surfaces where a flat finish is desired. NOTE: Not for use in areas that are frequently washed or scrubbed. Ideal for rental property.					
Surface Preparation:		<p>New Work: The surface to be coated must be clean and free of dust, grease, wax, rust, oil, and bleeding stains.</p> <p>Priming – Drywall – Self priming, but for best results use 4190 Latex Primer Sealer Plaster – For best results use No. 50 Block-Out, 5790 Pro Prime Primer Sealer. Wood – Alkyd Primer Undercoat 37-11 Ferrous Metal – Rust inhibiting metal primer such as 35-111, 2090 or 925-147. Galvanized – 36-11 or 180-11 Masonry – Use Primer Sealer 43-10 or 48-11. To fill porous block use 946-11 or 529-11 Latex Block Filler.</p> <p>Repaint Work: On previously painted surfaces in good repair, no priming is generally necessary. On glossy surfaces remove the sheen with sandpaper or steel wool. Patch holes or cracks with appropriate filler. Spot prime bare areas with indicated primer. Remove any oil, chalk, dirt, wax or dust prior to re-coating. Any loose or flaking paint should be removed and the edges feather sanded to produce a smooth, uniform surface.</p>						
Application:		Stir product thoroughly with a circular, lifting motion to disperse into a homogenous liquid. Roller – 3/8" to 1-1/4" nap, depending on surface texture. Brush – Nylon or polyester filament Airless Spray – Tip size at atomization pressures will vary with type of equipment, viscosity and temperature. An orifice of .017 - .019 will provide the most satisfactory spray pattern. Best results are more likely obtained by using quality application tools. Do not apply directly over chalky surfaces or bleeding stains.						
NOTE: Formulated without mercury or lead.								

Resin Type:	Vinyl Acetate Acrylic
Solids:	Weight – 45.4% Volume – 30.3%
Weight Per Gallon:	10.88 lbs.
Viscosity:	105 ± 5 (Krebs Units)
Specular Gloss:	0 – 3% @ 85 Degrees
Recommended Film Thickness:	Wet – 3.5 to 4.5 mils Dry – 1.0 to 1.3 mils
VOC – VOS Statement:	This product contains less than 0.42 lbs or 50 GPL per gallon.
Cautions:	CAUTION! Do not take internally. Close container after each use. KEEP OUT OF REACH OF CHILDREN.

