



Clear Acrylic Coating

1290

SECTION NO. 4 ADS-505

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
Acrylic	Gloss *See Below	300-500 Sq Ft Per Gallon	Brush, Roller, or Spray	Clean Water	Warm Soapy Water	1-2 Hours	4 Hours	30 Days
PRODUCT NAME: 1290 Clear Acrylic Coating		This clear, water thinned sealer offers deep penetration into stucco, concrete and masonry surfaces. It will form a tough invisible film that repels water and helps reduce spalling and dusting. Will seal and refurbish a paint film that is showing signs of fading due to oxidation. Produces maximum intercoat adhesion between paint films. For interior or exterior use. Not designed as a clear finish for wood.						
WHERE TO USE:		Concrete Stucco Paint Additive	On interior or exterior surfaces such as walls, floors and existing paint finishes. Add to latex products for increased wet edge, adhesion, scrubability, penetration, ease of application, additional gloss or additional spread rate.					
Surface Preparation:		Surface must be clean and free of all oil, grease, excessive chalk, dust and dirt. Dirt and chalk should be removed by scrubbing with warm soapy water and thoroughly rinsed with clean water. Neutralize efflorescence by acid etching and mold or mildew by scrubbing thoroughly with a solution of one part household bleach, one part T.S.P. and three parts warm water. Rinse well with clean water following the etch or wash.						
Application:		Stir product thoroughly prior to painting. *This clear sealer is a concentrate and may be reduced as much as 1 to 1 to achieve desirable penetration and gloss level. Apply a flood coat by brush, roller or spray at a spread rate of 300 to 500 square feet per gallon. Take care to insure 100% coverage of the surface. Do not use outside if temperatures are below 50° F or if rain is threatening. Test a small area to insure desired results when applying over previously coated surfaces.						
NOTE: Formulated without mercury or lead.								

Resin Type:	Acrylic
Solids:	Weight – 30.1% Volume – 27.9%
Weight Per Gallon:	8.6 lbs.
Viscosity:	100 – 105 (Krebs Units)
Specular Gloss:	60% ± @ 60 degrees
Recommended Film Thickness:	Wet – 3.0 to 3.5 mils Dry – 0.8 to 1.0 mils
VOC – VOS Statement:	This product contains less than 2.9 lbs or 350 GPL per gallon.
Cautions:	CAUTION! Do not take internally. Close container after each use. KEEP OUT OF REACH OF CHILDREN.