



KITCHEN & BATH SEMI-GLOSS ENAMEL

192 LINE

SECTION NO. 2 ADS 348

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
100% Acrylic	Semi-Gloss	350-400 Sq Ft Per Gallon	Brush, Roller, or Spray	Clean Water	Warm Soapy Water	30 Minutes	4 Hours	7-10 Days
PRODUCT NAME: 192 LINE KITCHEN & BATH SEMI-GLOSS ENAMEL		Kitchen & Bath Acrylic Semi-Gloss Enamel is a premium water based enamel, formulated for use in areas subjected to high humidity, condensation, changing temperatures and harsh wear. The cured film is mildew proof, blister proof, non-yellowing, and very durable.						
WHERE TO USE:		Metal Interior/Exterior. Recommended for use in kitchens, baths, laundries and other rooms subjected to high humidity. Wood Masonry Drywall						
Surface Preparation:		<p>New Work: The surface to be coated must be clean and free of oil, grease, rust and other contaminants that could interfere with adhesion.</p> <p>Priming - - - Ferrous Metal – Rust Scat Primer 36-11, 35-111, 35-147 or 35-153. Non-Ferrous Metal – Perma Bond 100-10 Galvanized – Use Perma Bond 100-10 or 36-11 Wood Interior – Latex Undercoat 78-11 or Alkyd Undercoat 37-11 Wood Exterior – Latex Primer 410-11 (Use for wood trim & doors only) #2090 Drywall / Plaster – Latex Primer Sealer 40-11, #50 Block-It Concrete – Self Priming or Block Filler 946-11 or Masonry Sealer 43-11</p> <p>Repaint: The surface to be painted must be clean and free of dirt, chalk, wax, grease, rust or loose flaking paint. Dirt and chalk should be removed by scrubbing with warm soapy water and thoroughly rinsed with clean water. Wax should be removed by solvent cleaning. Grease should be cleaned by using Coronado Sur-Prep I. Rust must be removed by hand sanding vigorously or by conscientious power tool cleaning. Remove loose paint by scraping. Feather sand rough edges to insure a smooth finish coat. Glossy surfaces must be dulled by lightly sanding. Remove sanding dust before paint application. Any exposed substrate should be spot primed with the appropriate primer.</p>						
Application:		Stir thoroughly with a circular, lifting motion to assure even pigment dispersion. Roller – Use a short nap enameling cover. Brush – Use a polyester or nylon filament brush. Spray – May be sprayed using conventional or airless equipment. Can be thinned with clean water up to 20% for spraying. For best results use quality applicator tools. Do not sacrifice good results by using inexpensive tools. Apply only when surface and air temperatures are between 50° - 90° F.						
NOTE: Formulated without mercury or lead.								

Resin Type:	Acrylic 100%
Solids:	Weight - 51.0% Volume - 37.1%
Weight Per Gallon:	10.70 lbs.
Viscosity:	90 – 100 (Krebs Units)
Specular Gloss:	40 – 45% @ 60 Degrees
Sag Rating:	Pass 8 mils (Lenetta)
Recommended Film Thickness:	Wet - 3.0 to 4.0 mils Dry - 1.0 to 1.5 mils
Light Reflectance:	95% (White or lightest colors)
Cautions:	CAUTION: Do not take internally. Close container after each use. KEEP OUT OF REACH OF CHILDREN.
VOC – VOS Statement:	This product contains a maximum of 2.0 lbs. VOC/VOS per gallon of coating.