



PRO - TECH SATIN
100% Acrylic
Exterior Latex
4800 LINE

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
100% Acrylic Latex	Satin	Up to 400 Sq Ft Per Gallon	Brush, Roller, Pad or Spray	Clean Water	Warm Soapy Water	60 Minutes	4 Hours	10-14 Days
PRODUCT NAME: 4800 PRO-TECH 100% Acrylic Exterior Latex Satin		This latex house paint is designed for service over new or previously painted surfaces in good condition. It is formulated to cover most surfaces in one coat when applied at the rate of 400 sq ft per gallon. Latex House Paint dries dust and bug free in one hour. Provides a durable and protective finish on any properly primed and prepared exterior surface.						
WHERE TO USE:		Wood On exterior siding, foundations, facia, shutters or retaining walls. Masonry Hardboard Metal Galvanized Aluminum Siding						
Surface Preparation:		<p>When air temperature is at 35°F, substrates may be colder; prior to painting, check to be sure the air, surface, and material temperature are above 35°F and at least 5°F above the dew pint. Avoid using if rain or snow is expected.</p> <p>Surface to be painted must be clean and free of dirt, chalk, wax, grease, rust or loose, flaking paint. Dirt and chalk should be removed by power washing, or hand scrubbing, with an abrasive cleanser and water, followed by a clean water rinse. Wax should be removed by solvent cleaning. Grease and oil should be cleaned by using Coronado Sur-Prep 1. Rust must be removed by blasting, hand sanding vigorously or by conscientious power tool cleaning. Remove loose paint by scraping. Feather sand rough edges to insure a smooth finish coat. Glossy surfaces must be dulled by lightly sanding. Remove sanding dust before paint application. Any exposed substrate should be spot primed with the appropriate primer.</p> <p>Priming – (new or bare surfaces) WOOD – Use O’Leary Exterior Acrylic Primer #2090 or #560 Oil Primer. MASONRY – Use O’Leary #4790. To fill porous block, use #529-11. FERROUS METAL – Rust Inhibiting Metal Primer such as O’Leary #2090. NON-FERROUS METAL – Use O’Leary #2090. GALVANIZED – Use O’Leary #2090.</p>						
Application:		Stir product with a circular, lifting motion before you begin to paint. May be applied by brush, spray, pad or roller at a rate of up to 400 sq ft per gallon. Surface texture and porosity will affect actual yield. For best brush application results, use a quality synthetic filament brush. For the roller application, 3/8” nap cover. For spray application, thin with clean water, up to 10% reduction if necessary. Do not apply to hot surfaces or in direct sunlight. Do not apply if rain is threatening.						
NOTE: Formulated without mercury or lead.								

Resin:	100% Acrylic
Solids:	Weight – 41.5% Volume – 32.2%
Weight Per Gallon:	9.94 lbs.
Viscosity:	92 – 95 (Krebs Units)
Specular Gloss:	15 - 22 @ 60 Degrees
Recommended Film Thickness:	Wet – 3.5 to 4.0 mils Dry – 1.6 to 1.9 mils
VOC – VOS Statement:	This product contains less than 1.09 lbs. or 130 GPL per gallon.
Cautions:	CAUTIONS! Do not take internally. Close container after each use. KEEP OUT OF REACH OF CHILDREN.

Revised 04/2016

