



**LATEX DRY FALL
FLAT & SEMI-GLOSS**

5000 - 2900

SECTION NO. 6 ADS 709

| Type | Sheen | Spread Rate | Recommended Application | Thinner | Clean Up | DRY TIME | | |
|---|-----------------|---|---|-------------|------------------|------------|---------|--------|
| | | | | | | Tack Free | Re-coat | Cure |
| Vinyl Acrylic | Flat Semi-Gloss | Up to 450 Sq Ft Per Gallon | Spray Only | Clean Water | Warm Soapy Water | 45 Minutes | 4 Hours | 7 Days |
| PRODUCT NAME: 5000, 2900 LATEX DRY FALL Flat & Semi-Gloss | | Latex Dry Fall is formulated for spray application to interior ceilings, walls and structural members in commercial and institutional buildings. The over-spray dries to a dust before reaching the floor. This feature reduces the cost of masking and covering procedures. | | | | | | |
| WHERE TO USE: | | Drywall Plaster Metal Concrete | On interior ceilings, walls and structural members. This dryfall finish can be re-coated in 4 hours on new or repaint work. | | | | | |
| Surface Preparation: | | <p>All surfaces to be coated must be clean and free of dust, dirt, chalk, grease, oil, wax, loose paint, form oils, and any other contaminates that would be detrimental to proper adhesion. Remove all loose, scaly paint by sanding thoroughly. Surface chalk must be removed by scrubbing with warm soapy water and thoroughly rinsing. Glossy surfaces must be dulled by thoroughly sanding with steel wool. Any exposed substrate should be spot primed with the appropriate primer.</p> <p>Primers – Steel – Metal Primers: 35-111 or 2090 Non-Ferrous Metal: 100-10 Perma Bond Primer Wood – C37-11 Undercoater Concrete Block – C946-11 Latex Block Filler Poured Concrete – 4190 Latex Primer Galvanized – 36 – 11 or 180-11</p> | | | | | | |
| Application: | | Stir product thoroughly prior to painting. Apply by airless or conventional spray. Square footage varies with surface & application. Changes in relative humidity will cause significant differences in the distance required for dry fall characteristics. At 50% relative humidity the product will dry fall at 8 feet. However, at 90% relative humidity, as much as 15 feet will be necessary for over-spray to dry. Do not apply when temperature is below 50° F. Thinning is not generally necessary. If required, use clean water sparingly. | | | | | | |
| NOTE: Formulated without mercury or lead. | | | | | | | | |

| | | | | | | | | | | |
|------------------------------------|--|--------------------|-------------|--------------------|----------|-------|-------|----------|-------|-------|
| Resin: | Vinyl Acrylic | | | | | | | | | |
| Solids: | <table> <tr> <td></td> <td>5000</td> <td><u>2900</u></td> </tr> <tr> <td>Weight -</td> <td>54.7%</td> <td>41.8%</td> </tr> <tr> <td>Volume -</td> <td>34.9%</td> <td>26.6%</td> </tr> </table> | | 5000 | <u>2900</u> | Weight - | 54.7% | 41.8% | Volume - | 34.9% | 26.6% |
| | 5000 | <u>2900</u> | | | | | | | | |
| Weight - | 54.7% | 41.8% | | | | | | | | |
| Volume - | 34.9% | 26.6% | | | | | | | | |
| Weight Per Gallon: | 5000: 11.59 lbs 2900: 10.15 lbs | | | | | | | | | |
| Viscosity: | 70 – 80 (Krebs Units) | | | | | | | | | |
| Specular Gloss: | 5000: 1 – 2% @ 85 Degrees 2900: 40 – 50% @ 60 Degrees | | | | | | | | | |
| Recommended Film Thickness: | Wet – 3.0 to 4.0 mils Dry – 1.1 to 1.5 mils | | | | | | | | | |
| VOC – VOS Statement: | This product contains less than 3.33 lbs. or 400 GPL per gallon. | | | | | | | | | |
| Cautions: | <p style="text-align: center;">CAUTION ! COMBUSTIBLE ! Contains Alcohol</p> <p>Keep away from heat & flame. To avoid breathing vapors or spray mist, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches or dizziness, increase fresh air or wear respiratory protection (NIOSH/MSHA TC23C) or equivalent) or leave the area. Close container after each use. Avoid contact with skin. Use with adequate ventilation.</p> <p>NOTICE: Reports have associated repeated and prolonged occupational over-exposure to solvents with permanent brain & nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal.</p> <p style="text-align: center;">KEEP OUT OF REACH OF CHILDREN.</p> | | | | | | | | | |