



**Pro Prime  
BLOCK FILLER  
Interior / Exterior Latex  
529 – 11**  
SECTION NO. 3 ADS 405

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
Acrylic Latex	Flat	Up to 50-100 Sq Ft Per Gallon	Brush, Roller, Or Airless Spray	Clean Water	Warm Soapy Water	1 Hour	4 Hours	7 Days
<b>PRODUCT NAME:</b> 529-11 PRO PRIME BLOCK FILLER INTERIOR / EXTERIOR LATEX		This Latex Block Filler is formulated with heavy pigmentation and high resin content, allowing it to fill concrete block in one brush, roller or spray coat, when applied at the rate of 75 sq ft per gallon. This product complies with LEED Green Building Rating System GS-11 for interior flat paints.						
<b>WHERE TO USE:</b>		Cement Concrete Masonry Blocks	On interior or exterior cementacious substrates where a smooth, uniform surface is desired. New cementacious substrates should cure at least 30 days. PH must be 11.0 or lower. For PH greater than 11.0 apply 5090 Masonry Barrier Coat.					
<b>SURFACE PREPARATION:</b>		Surface to be painted must be clean and free of dust, grease, wax and rust stains. Prior to painting any mildewed surface, thoroughly remove the mildew by scrubbing with a strong solution of non-ammoniated cleanser (or T.S.P.) and warm water with 8 oz. of bleach per gallon. Rinse thoroughly and allow to dry.						
<b>APPLICATION:</b>		Stir product with a circular lifting motion. This block filler may be brushed, rolled or sprayed. Apply generously as it comes from the container. Conventional or airless spray application procedures may be used with this product. Care must be taken to assure that large voids are filled during spray application. Back rolling with a dry roller is recommended for a more uniform fill. A conventional "D" or airless .025 - .030" fluid tip should be used for spray application. Do not apply when surface or air temperatures are below 50°F Latex Block Filler may be thinned sparingly with clean water to proper spray consistency. Thinning is not normally required for brush or roller application. A second coat may be applied if required. <b>IMPORTANT:</b> If Epoxy is to be the finish coat, it is strongly recommended that the surface be squeegeed immediately after the application to force more material into the pores of the block and remove the surface coating of block filler to the extent that at least 50% of the block surface is exposed for direct contact of epoxy to block						
<b>NOTE: Formulated without mercury or lead.</b>								

<b>RESIN TYPE:</b>	Vinyl Acrylic / Acrylic
<b>SOLIDS:</b>	Weight – 61.0% Volume – 41.3%
<b>WEIGHT PER GALLON:</b>	12.5 lbs.
<b>VISCOSITY:</b>	122-128 (Krebs Units)
<b>FLASH POINT:</b>	200° F or over (TT-P-141, Method 4293)
<b>SPECULAR GLOSS:</b>	0 – 5% @ 85 Degrees
<b>SAG RATING:</b>	Pass 26 mils (Lenetta)
<b>LIGHT REFLECTANCE:</b>	N / A
<b>RECOMMENDED FILM THICKNESS:</b>	Wet – 16.0 – 20.0 Mils Dry – 8.4 – 10.5 Mils
<b>VOC – VOS STATEMENT:</b>	This product contains 26 grams per liter.
<b>CAUTIONS:</b>	<p><b>CAUTION!</b></p> <p>Do not take internally. Close container after each use.</p> <p><b>KEEP FROM FREEZING.</b></p> <p><b>KEEP OUT OF REACH OF CHILDREN.</b></p>

REV. 08/2012

ADS 405

