



**FILL AND FINISH
VINYL / ACRYLIC
LATEX SATIN BLOCK FILLER
539 - 11
SECTION NO. 2 ADS 350**

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
Vinyl Acrylic Latex	Satin	Up to 75 Sq Ft Per Gallon	Brush, Roller, Or Airless Spray	Clean Water	Warm Soapy Water	30 Minutes	8 Hours	7 - 10 Days
PRODUCT NAME: 539-11 Hi-Hide Vinyl/Acrylic Latex Satin Block Filler		This Latex Satin Block Filler is formulated with high resin content, allowing it to fill concrete block in one brush, roller or spray coat, when applied at the rate of 75 sq ft per gallon.						
WHERE TO USE:		Cement Concrete Masonry Blocks	On interior or cementacious substrates where a smooth, uniform satin finish is desired.					
Surface Preparation:		Surface to be painted must be clean and free of dust, grease, wax and rust stains. Prior to painting any mildewed surface, thoroughly remove the mildew by scrubbing with a strong solution of non-ammoniated cleanser (or T.S.P.) and warm water with 8 oz. of bleach per gallon. Rinse thoroughly and allow to dry.						
Application:		Stir product with a circular lifting motion. This block filler may be brushed, rolled or sprayed. Apply generously as it comes from the container. Conventional or airless spray application procedures may be used with this product. Care must be taken to assure that large voids are filled during spray application. Back rolling with a dry roller is recommended for a more uniform fill. A conventional "D" or airless .025 - .030" fluid tip should be used for spray application. Do not apply when surface or air temperatures are below 50°F Latex Block Filler may be thinned sparingly with clean water to proper spray consistency. Thinning is not normally required for brush or roller application. A second coat may be applied if required.						
NOTE: Formulated without mercury or lead.								

Resin Type:	Vinyl Acrylic / Acrylic
Solids:	Weight – 55.0% Volume – 41.5%
Weight Per Gallon:	10.6 lbs.
Viscosity:	117-125 (Krebs Units)
Flash Point:	200° F or over (TT-P-141, Method 4293)
Specular Gloss:	20 –25% @ 60 Degrees
Sag Rating:	Pass 20 mils (Lenetta)
Recommended Film Thickness:	Wet – 16.0 – 20.0 Mils Dry – 8.4 – 10.5 Mils
VOC – VOS Statement:	This product contains less than 2.08 lbs or 250 GPL per gallon.
Cautions:	CAUTION: Do not take internally. Close container after each use. KEEP FROM FREEZING KEEP OUT OF REACH OF CHILDREN.