



**O SCRUB
LATEX FLAT
6800 Line**

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
Vinyl Acrylic	Flat	Up to 400 Sq Ft Per Gallon	Brush, Roller, Pad or Airless Spray	Clean Water	Warm Soapy Water	30 Minutes	4 Hours	30 Days
PRODUCT NAME: 6800 O Scrub Flat		A top grade interior latex flat wall paint formulated to hide most substrates in one coat when applied at up to 400 square feet per gallon. It may be washed without harming the film. Finger prints, soil and grease wash off with mild soap and water. A spatter resistant formulation with excellent flow and leveling.						
WHERE TO USE:		Drywall Plaster Wood Masonry This flat latex wall paint imparts a lusterless, aesthetically pleasing finish, available in over 1,000 colors. It is an ideal finish for living rooms, dining rooms, bedrooms or anywhere a flat finish is desirable.						
Surface Preparation:		New Work: The surface to be coated must be clean and free of dust, grease, wax, rust, oil and bleeding stains. Priming – Drywall – Self priming, but for best results use 4190 Latex Primer Sealer. Plaster - For best results use #50 Block It or 5790 Pro Prime Primer/Sealer. Wood – Alkyd Primer Undercoat 37-11 or 0590. Ferrous Metal – Rust Inhibiting Metal Primer such as 35-111 or 2090. Non-Ferrous Metal – Perma Bond 100-10. Galvanized – Acrylic Primer 36-11 or 100-10. Masonry – Use Primer Sealer 43-10 or 48-11. To fill porous block use 946-11 Latex Block Filler. Repaint Work: On previously painted surfaces in good repair, no priming is generally necessary. On glossy surfaces remove the sheen with sandpaper or steel wool. Patch holes or cracks with appropriate filler. Spot prime bare areas with indicated primer. Remove any oil, chalk, dirt, wax or dust prior to recoating. Any loose or flaking paint should be removed and the edges feather sanded to produce a smooth, uniform surface.						
Application:		Stir product thoroughly with a circular, lifting motion to disperse into a homogenous liquid. Roller – 3/8" to 1 1/4" nap, depending on surface texture. Brush – Nylon or polyester filament. Airless Spray – Tip at atomization pressures will vary with type of equipment, viscosity and temperature. An orifice of .017 - .019 will provide the most satisfactory spray pattern. Best results are more likely obtained by using quality application tools. Do not apply directly over chalky surfaces or bleeding stains.						
NOTE: Formulated without mercury or lead.								

Resin:	Vinyl Acrylic
Solids:	Weight 52.5 % Volume 35.7 %
Weight Per Gallon:	11.33 lbs.
Viscosity:	108 – 112 (Krebs Units)
Specular Gloss:	1 – 3% @ 85 degrees
Recommended Film Thickness:	Wet – 3.5 to 5.0 mils Dry – 1.3 to 1.5 mils
VOC – VOS Statement:	This product contains less than 0.83 lbs. per gallon or 100 G.P.L.
Cautions:	<p>CAUTION!</p> <p>Do not take internally. Close container after each use.</p> <p>KEEP OUT OF REACH OF CHILDREN.</p> <p>KEEP FROM FREEZING.</p>