



PRESERVE

PRESERVE Latex / Eggshell Finish

Bonaire.....P0250
 Hearthstone.....P0550
 SheepskinP0650
 Awakening.....P1050

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
Vinyl Acrylic	Eggshell Enamel	Up to 400 Sq Ft Per Gallon	Brush, Roller, Pad or Airless Spray	Clean Water	Warm Soapy Water	60 Minutes	4 Hours	7 Days
PRODUCT NAME: PRESERVE LATEX / EGGSHELL ENAMEL		Preserve Eggshell Enamel is designed to be applied with equal success by contractors or do-it-yourselfers. It applies easily without spattering, covers most surfaces in one coat and may be washed repeatedly without film damage. Perfect for children's bedrooms, hallways or wherever a low sheen is desirable.						
WHERE TO USE:		Drywall Plaster Wood Metal Masonry	Preserve Latex Eggshell can be applied to walls, woodwork, trim, paneling, doors or dados. It is a good choice for interior bedrooms, family rooms, hallways, recreation rooms, commercial or rental properties.					
SURFACE PREPARATION:		<p>New Work: The surface to be coated must be clean and free of dust, grease, wax, rust, oil, and bleeding stains.</p> <p>Priming: Drywall –For best results use #4190 Latex Primer Sealer or 7190. Plaster – For best results use #50 Block It Wood – Alkyd Primer Undercoat #37-11 Ferrous Metal – Rust inhibiting metal primer such as #35-111, #925-147. Galvanized/Non-Ferrous - #36-11 or #180-11. Masonry – Masonry Sealer #43-10 or #48-11. To fill porous block use #529-11 Latex Block Filler.</p> <p>Repaint Work: On previously painted surfaces in good repair, no priming is generally necessary. On glossy surfaces, remove the sheen with sandpaper or steel wool. Patch holes or cracks with appropriate filler. Spot prime bare areas with indicated primer. Remove any oil, chalk, dirt, wax or dust, prior to re-coating. Any loose or flaking paint should be removed and the edges feather sanded to produce a smooth, uniform surface.</p>						
APPLICATION:		<p>Stir product thoroughly with a circular, lifting motion to disperse into a homogenous liquid.</p> <p>Roller – 3/8" to 1-1/4" nap, depending on surface texture. Brush – Nylon or polyester filament. Airless Spray – Tip size at atomization pressure will vary with type of equipment, viscosity and temperature. An orifice of .017 - .019 will provide the most satisfactory spray pattern.</p> <p>Best results are more likely obtained by using quality application tools. Do not apply directly over chalky surfaces or bleeding stains.</p>						
NOTE: Formulated without mercury or lead.								

RESIN TYPE:	Vinyl Acrylic
SOLIDS:	Weight – 51.0% Volume – 38.3%
WEIGHT PER GALLON:	10.8 lbs.
VISCOSITY:	102 – 105 (Krebs Units)
SPECULAR GLOSS:	5 – 10% @ 60 Degrees
RECOMMENDED FILM THICKNESS:	Wet – 4.0 to 4.5 mils Dry – 1.7 to 1.9 mils
VOC – VOS STATEMENT:	These products contain a maximum of 150 g/L.
CAUTIONS:	CAUTION! Do not take internally. Close container after each use. KEEP OUT OF REACH OF CHILDREN.



PRESERVE

