



TTM - LG
00 - White
10 - Midtone
15 - Deep
18 - Neutral
Section 18 IMA LG

Type	Sheen	Recommended Application	Thinner	Clean Up	DRY TIME		
					Tack Free	Re-coat	Cure
Alkyd	Satin	Conventional, Airless, Air Assisted Airless	Xylene	Xylene	20 Minutes	2 Hours	7 Days
PRODUCT NAME: TTM LG 00 10 15 18		High quality gloss alkyd enamel line for interior or exterior use, that dries to touch in 20 minutes. This high hiding enamel produces a very serviceable finish.					
WHERE TO USE:		TTM LG can be used on any properly prepared interior or exterior surface. For use on wood, galvanized and aluminum surfaces, a primer is required.					
Surface Preparation:		All surfaces should be cleaned and free of contaminants. Do not apply directly over chalky surfaces. Glossy surfaces must be de-glossed by abrasion or liquid de-glosser. Surface areas are to be "completely dry." Do a test patch area to determine if lifting of the old film is apparent. If lifting or wrinkling occurs, use a proper sandwich primer.					
Application:		TTM LG is formulated to spray with most airless and air assisted airless spray equipment. A slight reduction may be required when using conventional spray and HVLP guns.					
Thinner and Clean-Up		Use Xylene to thin. Thinning may affect product performance. Equipment and tools should be cleaned immediately.					
NOTE: Formulated without mercury or lead.							

Viscosity:	70 – 75 K.U.															
Weights Per Gallon:	00 – 10.76 10 – 10.27 15 – 9.94 18 – 9.24															
Specific Gravity:	00 – 1.29 10 – 1.23 15 – 1.19 18 – 0.11															
Solids:	<table> <thead> <tr> <th></th> <th><u>Wt %</u></th> <th><u>Vol. %</u></th> </tr> </thead> <tbody> <tr> <td>00 -</td> <td>60.32</td> <td>41.13</td> </tr> <tr> <td>10 -</td> <td>57.29</td> <td>39.53</td> </tr> <tr> <td>15 -</td> <td>55.61</td> <td>39.20</td> </tr> <tr> <td>18 -</td> <td>50.33</td> <td>36.75</td> </tr> </tbody> </table>		<u>Wt %</u>	<u>Vol. %</u>	00 -	60.32	41.13	10 -	57.29	39.53	15 -	55.61	39.20	18 -	50.33	36.75
	<u>Wt %</u>	<u>Vol. %</u>														
00 -	60.32	41.13														
10 -	57.29	39.53														
15 -	55.61	39.20														
18 -	50.33	36.75														
V.O.C.	00 - 512 G/L 10 - 526 G/L 15 - 529 G/L 18 - 550 G/L															
Color:	Full Range of Colors															
Gloss:	When used with TTM, any 60° Gloss between 20 and 90, can be achieved.															
Dry Time:	20 Min. Tack Free 2 Hours to Recoat 7 days Complete Cure															